

鋁摩擦攪拌點焊的靜態破壞機制

李憲章、王東安、李佳言

E-mail: 9511032@mail.dyu.edu.tw

摘要

摩擦攪拌點焊(spot friction welds, SFW)是一項新的接合製程技術。根據實驗觀察，探討摩擦攪拌點焊對於6061-T6鋁合金板材焊點的顯微結構以及缺陷。使用不同的焊接參數來結合鋁板，並且利用光學顯微鏡來觀察摩擦攪拌點焊在拉伸試驗破壞前與破壞後的焊點截面。實驗觀察顯示，在拉伸負載的情況下，裂痕是從焊點中心靠近攪拌區的地方開始出現，沿著焊點延伸至表面最後破裂。

關鍵詞：摩擦攪拌點焊，拉伸試驗，破壞，微結構

目錄

封面內頁 簽名頁 授權書.....	iii	中文摘要.....	iv	英文摘要.....	v
謝.....	vi	目錄.....	vii	圖目錄.....	ix
表目錄.....	xi	第一章 緒論.....	1	第二章 文獻回顧 2.1 基材6061-T6鋁合金板材質特性.....	3
2.2 摩擦攪拌點焊.....	3	2.3 摩擦攪拌點焊技術的特色.....	4	2.4 摩擦攪拌點焊之參數.....	7
2.5 摩擦攪拌點焊微觀組織分佈.....	9	2.6 再結晶及其相關行為.....	10	2.7 應用成果.....	11
第三章 實驗步驟 3.1 實驗基材.....	12	3.2 焊接機台架設與夾具的設計.....	12	3.3 隔熱墊板的選用.....	15
3.4 攪拌桿的桿材選用.....	16	3.4.1 鹽浴法.....	17	3.5 攪拌桿幾何尺寸設計.....	17
3.6 實驗步驟.....	18	3.7 金相實驗.....	19	3.8 微硬度實驗.....	20
3.9 拉伸實驗.....	21	第四章 結果與討論 4.1 焊接參數.....	22	4.2 金相實驗.....	23
4.3 拉伸實驗破壞斷面分析.....	24	4.4 微硬度實驗.....	25	4.5 焊接力對於摩擦攪拌點焊焊接的影響.....	26
第五章 結論.....	28	參考文獻.....	55		

參考文獻

- [1] P.-C. Lin, S.-H. Lin, J. Pan, T. Pan, J.M. Nicholson, M.A. Garman, 2004, Microstructures and failure mechanisms of spot friction welds in lap-shear specimens of aluminum 6111-T4 sheets, SAE Technical Paper no. 2004-01-1330, Society of Automotive Engineering, Warrendale, PA.
- [2] P. Thornton, A. Krause, R. Davies, Aluminum spot weld, 1996, Welding Journal 75 101s-108s.
- [3] A. Gean, S.A. Westgate, J.C. Kuczka, J.C. Ehrstorm, 1999, Static and fatigue behavior of spot-welded 5182-0 aluminum alloy sheet, Welding Journal 78 80s-86s.
- [4] R. Sakano, K. Murakami, K. Yamashita, T. Hyoe, M. Fujimoto, M. Inuzuka, U. Nagao, H. Kashiki, 2001, Development of spot FSW robot system for automobile body members, in: Proceedings of the 3rd international symposium of friction stir welding, Kobe, Japan.
- [5] T. Iwashita, 2003, Method and apparatus for joining, US Patent 6601751 B2.
- [6] 賴耿陽譯，1987，鋁溶接技術，復漢出版社，1-7。
- [7] W.M. Thomas, E.D. Nicholas, J.C. Needham, M.G. Murch, P.T. Smith, C.J. Dawes, 1991, Friction welding, The Welding Institute, International Patent Application PCT/GB92/02203.
- [8] Y.S. Sato, H. Kokawa, M. Enomoto, S. Jogan T. Hashimoto, 1999, Precipitation sequence in friction stir weld of 6063 aluminum during aging, Metallurgical and Materials Transactions 30(12) 3125-3130.
- [9] S.H. Park, Y.S. Sato H. Kokawa, 2003, Effect of micro-texture on fracture location in friction stir weld of Mg alloy AZ61 during tensile test, Scripta Materialia 49 161-166.
- [10] 庾忠義，2003，超細晶鋁之機械性質，國立中山大學，博士論文，3-5。
- [11] K.E. Knipstorm, B. Pekkari, 1997, Friction stir welding process goes commercial, Welding Journal 76(9) 55-57.
- [12] 中國攪拌摩擦鋁中心，北京賽福斯特技術有限公司。 <http://www.cfswt.com/aspnews/fswt/2004528143838.htm> [13] P.J. Ditzel, J.C. Lippold, 1999, Influence on the tensile properties of friction stir welding in alloys 6061-T6, 5454-H34, and 2195-T8, Materials Joining Technology, EWI Project No. 012531RP, Report No. MR 019877.
- [14] Kh. A.A. Hassan, A.F. Norman, D.A. Price P.B. Prangnell, 2003, Stability of nugget zone grain structures in high strength Al-alloy friction stir welds during solution treatment, Acta Materialia 51 1923-1936.

- [15] S.W. Kallee, 1998, Knowledge based software package for friction stir welding, Cambridge, Proc. INALCO-7 209-217.
- [16] M.B. Stewart, G.P. Adamas, A.C. Nunes Jr., P. Romine, 1998, Developments in theoretical and applied mechanics, USA, Florida Atlantic University 19 472-484.
- [17] K. Colligan, 1999, Material flow behavior during friction stir welding of aluminum, *Welding Research* 78 229-237.
- [18] W.J. Arbegast, 2003, in: B. Radhakrishnan (Eds.), Hot deformation of aluminum alloys III, Z. Jin, A. Beaudoin, T.A. Bieler, TMS, Warrendale, PA, USA, 313.
- [19] G. Kohn, Y. Greenberg, I. Makover, and A. Munitz, 2002, Laser-assisted friction stir welding, American Welding Society, <https://www.aws.org/wj/2002/02/feature2> [20] P.J. Ditzel, J.C. Lippold, 1999, Microstructure property relationships in aluminum friction stir welds, TWI Report, August 1999 47-51.
- [21] R.E. Reed-Hil, R. Abbaschian, 1991, Physical metallurgy principles, PWS-Kent Publishing Company, 240-249.
- [22] K.V. Jata, S.L. Semiantin, 2000, Continuous dynamic recrystallization during friction stir welding of high strength aluminum, *Scripta Materialia* 43(8) 743-749.
- [23] H. Yamagata, Y. Ohuchida, N. Sato and M. Otsuka, 2001, Nucleation of new grains during discontinuous dynamic recrystallization of 99.998 mass% aluminum at 453K, *Scripta Materialia* 45(7) 1055-1061.
- [24] 蕭發富, 1998, 鋁合金板對接之攪拌摩擦銲接技術研究, 國立台北科技大學, 碩士論文, 13-33.
- [25] 黃振賢, 1995, 機械材料, 文京圖書, 208-210.
- [26] 黃振賢, 1985, 金屬熱處理, 文京圖書, 308.
- [27] L.E. Murr, G. Liu, J.C. McClure, 1998, A TEM study of precipitation and related microstructures in friction-stir-welded 6061 aluminum, *Journal of Materials Science* 33 1243-1251.
- [28] M. Boz, A. Kurt, 2004, The influence of stirrer geometry on bonding and mechanical properties in friction stir welding process, *Materials and Design* 25 343-347.
- [29] P.-C. Lin, S.-H. Lin, J. Pan, 2004, Modeling of plastic deformation and failure near spot welds in lap-shear specimens, SAE Technical Paper no. 2004-01-0817, Society of Automotive Engineering, Warrendale, PA.
- [30] S. Zuniga, S.D. Sheppard, 1997, Resistance spot weld failure loads and modes in overload conditions, *Fatigue and Fracture Mechanics: 27th Volume*, ASTM STP 1296, Piasek, R. S., Newman, J. C., and Dowling, N. E., Eds., American Society for Testing and Materials, 469-489.
- [31] S.-H. Lin, J. Pan, T. Tyan, P. Prasad, 2003, A general failure criterion for spot welds under combined loading conditions, *International Journal of Solids and Structures* 40 5539-5564.
- [32] W.Y. Chien, J. Pan, S.C. Tang, 2004, A combined necking and shear localization analysis for aluminum sheets under biaxial stretching conditions, *International Journal of Plasticity* 20 1953-1981.
- [33] H.J. Liu, H. Fujii, M. Maeda, K. Nogi, 2003, Tensile properties and fracture locations of friction-stir-welded joints of 2017-T351 aluminum alloy, *Journal of Materials Processing Technology* 142 692-696.